



RUST-OLEUM® FABRIC & VINYL

DESCRIPTION AND USES

Rust-Oleum® Fabric & Vinyl is a flexible coating that restores color on vinyl, simulated leather and some fabrics. This vinyl coating provides excellent adhesion that will not rub off, crack or peel. It is suitable for use on car seats, car door panels, dashboards, floor mats and other interior surfaces. Fabric & Vinyl features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

PRODUCTS

SKU	DESCRIPTION (11 ounce spray)
-----	------------------------------

248918	Gloss Black
248919	Flat Black
248920	Gray
248921	Sand
248922	Gloss White
248923	Gloss Red
248924	Gloss Blue
248925	Burgundy
248926	Silver
249307	Medium Blue
249308	Charcoal

PRODUCT APPLICATION

SURFACE PREPARATION

Clean surface with soap and water, rinse and let dry. If surface was previously treated with conditioners, waxes or other coatings, additional cleaning is required using either Rust-Oleum Paint Prep Wipe or mineral spirits. It is important that all residual coatings be removed from vinyl surfaces prior to application.

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 10-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Apply 2 or more light coats a few minutes apart. Do not use near open flame.

DRY & RECOAT


Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 10 minutes, to handle in 1 hour and is fully dry in 24 hours. Wait at least 6 hours before sitting on or using a painted object.

CLEAN-UP

Wipe off tip when finished. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

	TECHNICAL DATA	ATO-64
	RUST-OLEUM® FABRIC & VINYL	

PHYSICAL PROPERTIES

FABRIC & VINYL		
Resin Type	Acrylic Modified Vinyl Resin Solution	
Pigment Type	Varies with Color	
Solvents	Acetone, Ketones and Aromatic Hydrocarbons	
MIR	1.45 Max	
Fill Weight	11 ounces	
Recommended Dry Film Thickness (DFT) Per Coat	1.0-2.0 mils (25-50µ)	
Practical Coverage at Recommended DFT	10-12 sq. ft./can (0.90-1.09 m ² /can)	
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	10 minutes
	Recoat	1 hour
	Fully Dry	24 hours
Dry Heat Resistance	200°F (93°C)	
Shelf Life	5 years	
Flash Point	-156°F (-104°C)	
Safety Information	For additional information, see SDS	

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 866-585-8430
www.rustoleum.com/automotive

Form: GDH-117
Rev.: 080923