

Rust-Oleum Restore® 12X Stain & Sealant (Gallon)

Amounts recorded in: Ounces and 384th Ounce Increments

Golden Pine			
Colorant:		Oz.	384th
B	Lamp Black	0	54
C	Yellow Oxide	2	320
L	Raw Umber	0	32
MM	Magenta	0	90

Kona			
Colorant:		Oz.	384th
B	Lamp Black	0	288
C	Yellow Oxide	0	206
L	Raw Umber	1	51
MM	Magenta	0	78

Cedar			
Colorant:		Oz.	384th
B	Lamp Black	0	40
C	Yellow Oxide	2	0
I	Brown Oxide	0	132
MM	Magenta	0	42

Hickory			
Colorant:		Oz.	384th
C	Yellow Oxide	0	202
E	Phthalo Blue	0	24
I	Brown Oxide	1	120

Redwood			
Colorant:		Oz.	384th
C	Yellow Oxide	1	72
I	Brown Oxide	0	253
OO	Orange	0	46

Weathered Gray			
Colorant:		Oz.	384th
B	Lamp Black	0	190
C	Yellow Oxide	0	10
I	Brown Oxide	0	10
KX	White	0	306