



RUST-OLEUM® AUTOMOTIVE ENGINE PRIMER

DESCRIPTION AND USES

Rust-Oleum® Automotive Engine Primer bonds to bare metal and helps create a smooth surface for top coat application. It is formulated to prevent rust and is recommended for use on automotive engines and other automotive surfaces which reach intermittent temperatures up to 500°F (260°C). For maximum protection, top coat with Rust-Oleum Engine Enamel. Engine Primer features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

PRODUCT

| SKU | DESCRIPTION (12 oz. Aerosol) |
|--------|------------------------------|
| 249410 | Gray Engine Primer |

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

Wash the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and dry with a clean cloth. Remove loose paint and rust with a wire brush or sandpaper until the metal surface is completely bare. Lightly sand smooth and glossy surfaces.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to galvanized metal. Do not use on metal directly exposed to flames. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 12-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. For best adhesion, apply ONE thin coat. Do not apply a heavy coat or multiple coats of Auto Plastic Primer. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes and dries to handle in 1 hour. Top coat after 1 hour. Apply a second coat or top coat within 1 hour or after 48 hours.

CLEAN-UP

Wipe off tip when finished. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



**RUST-OLEUM® AUTOMOTIVE
ENGINE PRIMER**

PHYSICAL PROPERTIES

| | | ENGINE PRIMER |
|---|---------------|--|
| Resin Type | | Modified Alkyd |
| Pigment Type | | Titanium Dioxide |
| Solvents | | Acetone, Aliphatic and Aromatic Hydrocarbons |
| MIR | | 0.70 Max |
| Fill Weight | | 12 ounces |
| Recommended Dry Film Thickness (DFT) Per Coat | | 1.5-2.5 mils (37.5-62.5µ) |
| Practical Coverage at Recommended DFT | | 10-12 sq. ft./can (0.90-1.09 m ² /can) |
| Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity | Touch | 20 minutes |
| | Handle | 1 hour |
| | Recoat | Within 1 hour or after 48 hours |
| Dry Heat Resistance | | 500°F (260°C) Intermittent |
| Shelf Life | | 5 years |
| Flash Point | | -156°F (-104°C) |
| Safety Information | | For additional information, see SDS |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.