



ROCKSOLID® TEXTURED CLEAR TOPCOAT FLOOR COATING

DESCRIPTION AND USES

RockSolid® Textured Clear Topcoat Floor is textured protective coating designed to provide an anti-slip finish with excellent durability. It has excellent resistance to salt, oil, gasoline and other harsh chemicals. This floor coating can be used over any RockSolid Floor Coating.

PRODUCT FEATURES

- Low odor and can be applied indoors
- Longer pot life than other 100% solids epoxies
- Patented Easy Mix Burst Pouch Technology Pouch
- No hot tire pickup
- Satin finish with fine texture
- Drive on in 24 hours

KIT CONTENTS

- 2 Polycuramine Burst Pouches (Two part Burst Pouch Technology U.S. Patent Number 8,381,903 B2)
- 2 – ¼” Covers Roller
- Instructions

Items not supplied with the kit which need to be purchased separately:

- Roller Frame
- Extension Pole
- 3” Paint Brush

Other optional items that may be needed include:

- Stiff Bristled Broom or Scrub Brush
- Cleaner & Degreaser
- Concrete Etch

PRODUCTS

SKU	DESCRIPTION
317382	Clear Textured Satin TopCoat Kit
301939	Clear Textured Satin TopCoat Kit

PRODUCT APPLICATION

READ INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

Moisture Testing - New concrete should be allowed to cure for 30 days before application of any coating. If there is any doubt about the dryness of the concrete, conduct a test by simply taping a piece of 4 mil plastic sheet 2' X 2' on the bare concrete for 24 hours. Be sure to tape all four sides. After 24 hours, check the concrete for signs of moisture. The concrete substrate will be darker if damp. If moisture is found, allow additional drying time (10-14 days) and repeat the test.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

Testing for Sealer - Check for curing compounds or other types of sealers by pouring a small amount of water onto the concrete. If water soaks in, the surface is suitable for coating. If water beads up on the concrete, the surface is not porous and a test application is warranted to ensure proper adhesion will develop. Sanding or mechanical abrading may be required if proper adhesion does not develop.

Previously Coated Floors - If the floor has been previously coated, you need to determine if the coating is well adhered to the surface. If it is, you can coat over the previous coating if you completely de-gloss the surface using 40-80 grit sandpaper and wipe the surface down with MEK solvent. Make sure to wear proper protective equipment and follow the manufacturer's instructions.

For clear topcoat applications over newly coated surfaces, the coating will need to be dry to allow foot traffic. Do not walk of the coating while it is still tacky. Apply no earlier than 8-10 hours after coating with RockSolid Floor Coating and within 7 days. Ensure the surface is clean and dry prior to application.

Testing for Adhesion – With a razor knife, cut and X through the coating and down to the concrete. Apply a 5” piece of tape over the X and press down firmly. Completely remove the tape with one quick pull. If more than 25% of the taped area is removed, the original coating is not bonded well and needs to be removed chemically or mechanically with a grinder.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Loose/Damaged Concrete – If concrete is loose or chipped, the coating will not adhere properly. Repair damaged areas before applying RockSolid Textured Clear Topcoat.



ROCKSOLID® TEXTURED CLEAR TOPCOAT FLOOR COATING

PRODUCT APPLICATION (cont.)

CONCRETE PREPARATION – For coating over bare concrete

Scrub heavily soiled areas with RockSolid Heavy Duty Degreaser or Rust-Oleum Cleaner & Degreaser (sold separately). Scrub thoroughly, then rinse. Repeat as needed.

Use the concrete etch (sold separately) per the instructions to provide the proper surface condition to ensure proper adhesion. Rinse the floor thoroughly and allow it to dry completely.

CONCRETE PREPARATION – For coating over coated concrete

For clear topcoat applications over newly coated surfaces, the coating will need to be dry to allow foot traffic, do not walk on coating while it is still tacky. Apply no earlier than 8-10 hours after coating with RockSolid Floor Coating and within 7 days. Ensure the surface is clean and dry prior to application.

MIXING

MIX ONLY ONE POUCH AT A TIME. Both components and the environment should be pre-conditioned to a minimum of 40°F (4°C) prior to use. Be sure the air and surface temperatures are at least 5° above the dew point.

NOTE: RockSolid Textured Clear Topcoat must be applied within 7 days of the RockSolid Floor Coating.

Place a tarp on the ground and thoroughly mix the material in the pouch by shaking it both up and down and back and forth and squeezing each side of the pouch. Any clumps need to be massaged to break them up to ensure proper blending.

Combine the two components by placing the pouch on the ground and rolling it from the part A side towards the part B side like a tube of toothpaste. This will create pressure in the part A side and force the middle seal to burst, allowing the two components to mix together. Thoroughly mix the materials by shaking the pouch back and forth and squeezing the edges and corners toward the center of the pouch. Mix for 2-3 minutes. **Mix only one pouch at a time. The product is now activated and must be applied within 45 minutes to 1 hour.**

APPLICATION

Apply only when air, material and floor temperatures are between 40-90°F (4-32°C) and the relative humidity is below 80%. Extreme cold application temperatures may slow the cure time. **DO NOT** apply the coating if temperatures are expected to drop below 40°F for 48 hours after the application.

PRODUCT APPLICATION (cont.)

APPLICATION (cont.)

Once the material is thoroughly mixed, use scissors to cut a corner off the pouch. Pour the contents directly onto the floor in a 2-3" wide ribbon about 4' long. Trim the edges from the poured ribbon of material using a good quality synthetic brush.

Use a foam roller cover (included) and 9" roller frame to apply a thin coating evenly to the floor in 5' x 5' sections in an "M" and "W" pattern. De-lint the roller cover prior to application

Continue working in 5' x 5' sections. Occasionally stir or shake pouch to keep the product well mixed. Keep a wet edge to prevent lap marks or sheen differences. Only one coat is necessary over a coated floor (two coats are required when applying over bare concrete). Do not coat over control joints or roll over control joints. Use a flexible control joint fill material if desired. Repeat the above steps for each additional pouch.

COVERAGE RATE

Coated Concrete: Each Polycuramine pouch covers up to 200-250 square feet. Two pouches will cover up to 450-500 square feet (2.5 car garage).

Bare Concrete: Two pouches will cover up to 200-250 square feet with 2 coats. Coverage may vary based on condition and porosity of the concrete.

DRY TIME

Temperature and humidity may affect drying time. Do not walk on the coating while it is still tacky. Surface should be ready for foot traffic in 8-10 hours and vehicle traffic in 24-36 hours depending upon temperature and humidity.

CLEAN-UP

Clean tools and equipment with mineral spirits. Allow unused product to harden in the container and discard according to local regulations.

LIMITATIONS

This product must be installed at the specified spread rates to perform as described. Do not apply in direct sunlight. Do not apply product when the substrate and ambient temperatures are steadily below 40°F (4°C).

SHELF LIFE and STORAGE

Sixty (60) months in factory delivered unopened pouches. Keep away from extreme heat, cold and moisture. Maintain at a proper storage temperature of 45-90°F. Keep out of direct sunlight and away from fire hazards.

 <p>RUST-OLEUM® ROCKSOLID® THE WORLD'S TOUGHEST COATINGS™</p>	TECHNICAL DATA	RSD-52
ROCKSOLID® TEXTURED CLEAR TOPCOAT FLOOR COATING		

PHYSICAL PROPERTIES

		TEXTURED CLEAR TOPCOAT FLOOR COATING
Resin Type		Cycloaliphatic Amine Converted Urethane Modified Epoxy
Pigment		NA
Solvent		Benzyl Alcohol, 1-Chloro-4-(Trifluoromethyl) Benzene
Weight	Per Gallon	9.4 lbs.
	Per Liter	1.13kg
Solids By Volume		72.3%
Volatile Organic Compounds		<1 g/l
Practical Coverage		<p>Coated Concrete: Each Polycuramine pouch covers up to 200-250 square feet. Two pouches will cover up to 450-500 square feet (2.5 car garage).</p> <p>Bare Concrete: Two pouches will cover up to 200-250 square feet with 2 coats. Coverage may vary based on condition and porosity of the concrete. (coverage rate can vary depending on texture and porosity of concrete)</p>
Pot Life		45 minutes to 1 hour (depending on temperature and humidity)
Dry Times @ 70-80° F (21-27°C) and 50% Relative Humidity†	Tack Free	8-10 hours
	Dry Hard	12-16 hours
	Vehicle Traffic	24 hours depending on temperature
Shelf Life		60 months unopened factory delivered pouches
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

† Dry times will be increase if temperatures are less than 55°F (13°C).

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 800-373-6333
www.rustoleum.com/rocksolid

Form: GDH-1235
Rev.: 081122