

ROCKSOLID® CRACK & PATCH

DESCRIPTION AND USES

RockSolid® Crack & Patch is a fast setting, general purpose cement-based patching material for repairing concrete and masonry. Crack & Patch can be used to enhance the appearance of most concrete surfaces. Crack & Patch can be applied from a feather edge up to ½" thick to repair horizontal, vertical and overhead applications. It can be applied to concrete floors to level low spots before applying floor coverings such as wood or tile.

Primary applications include driveways, walkways, stairs, patios, pool decks, basement floors and garage floors.

PRODUCT FEATURES

- For repairs not greater than ½ inch
- Just add water to create a workable, easy to apply mixture
- Smooth creamy consistency
- Low shrinkage
- Trowel or float spread to a smooth coat
- Fast setting in 8-10 minutes
- Fix concrete blemishes
- Repair spalling and salt damage
- Can be shaped, molded and shaved down to help form applications
- Use to fill honey-comb or bug holes

PRODUCT

SKU DESCRIPTION (Concrete Gray 3 lb. bag)
60629 Crack & Patch

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

All surfaces must be structurally sound and non-flexing. Prepare the surface by removing all dust, waxes, sealers, old adhesive residue, curing compounds, oil or other foreign materials prior to the application. Dampen the area with clean water prior to the application. Do not leave puddles or standing water.

PRODUCT APPLICATION (cont.)

MIXING

Tear bag open by the notches on the sides. Add 1½ cups (10 ounces) of clean water per 3 pound bag. You may add up to ¾ cup (6 ounces) of additional clean water if needed. Squeeze the pouch to remove excess air. Zip the pouch closed and knead the bag for about 3 minutes until a lump-free consistency is achieved. If necessary, mix in a secondary container. Product will set in 8-10 minutes, so mix only amount needed.

APPLICATION

Crack & Patch is suitable for application at temperatures between 50° (10°C) and 100°F (38°C). Crack & Patch can be applied up to ½" thickness to repair horizontal, vertical or overhead concrete. Dampen or mist the area to be repaired. Force the material into the area with a trowel or by hand to secure a complete bond over the entire area to be repaired. Always slightly overfill the target repair area with Crack & Patch. Allow the material to set for approximately 8-10 minutes; then shave the material to follow the shape of the surrounding surface. Always shave toward the common bonding line between the repair mortar and the existing surface.

THINNING

Not required.

CLEAN-UP

Clean tools and equipment with water immediately after use. If the material has begun to harden, clean with warm soapy water.

KEEP OUT OF THE REACH OF CHILDREN AND ANIMALS. DO NOT TAKE INTERNALLY.

Form: GDH-967 Rev.: 080521



ROCKSOLID[®] CRACK & PATCH

PHYSICAL PROPERTIES

		CRACK & PATCH
Composition		Portland Cement, Aggregates, Additives
Solids	By Weight	100%
	By Volume	100%
Mixing Ratio		10 ounces of water to 3 lbs. of dry mixture
Induction Period		None required
Working Time		5-7 minutes @ 75-80°F (25-27°C)
Estimated Coverage*		1.5 square feet @ 1/4" thick
Dry Times @ 70-80°F (21-27°C) and 50% Relative Humidity	Initial Set	8-10 minutes
	Final Set	20-25 minutes
	Vehicle Traffic	2 hours
Shelf Life		24 months in dry unopened package
Safety Information		See SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation 11 Hawthorn Parkway Vernon Hills, Illinois 60061

Phone: 800-373-6333 www.rustoleum.com/rocksolid Form: GDH-967 Rev.: 080521