

• TRUSTED QUALITY SINCE 1921 •



**RUST-OLEUM®
CONCRETE & GARAGE RECOAT PRIMER**

DESCRIPTION AND USES

Rust-Oleum® Concrete & Garage Recoat Primer is an easy to use, revolutionary technology which allows you to coat over a previously coated or sealed concrete floor without having to scuff, sand, or grind the surface. Transform your worn garage, basement or patio floor with any Rust-Oleum floor coating (including water and solvent base).

PRODUCT FEATURES

- Use over sealed or previously coated surfaces - no sanding or grinding
- 1-Part water-based formula and low odor
- Prime and topcoat in 1 day
- 400 sq. ft./gal.
- Interior/Exterior

PRODUCT

SKU	DESCRIPTION (1 Gallon)
338806	Concrete & Garage Recoat Primer

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

For use on previously coated or sealed concrete floors in garages, carports, basements, laundry rooms, and other surfaces. May be applied to bare, etched concrete.

Note: This Concrete & Garage Recoat Primer is not a suitable replacement for etching a concrete surface. Proper surface preparation is critical for product performance.

LIMITATIONS

Do not use over superhydrophobic sealers or floors contaminated with tire seal and protectant products. Not recommended for asphalt.

Note: Concrete & Garage Recoat Primer is a gray color. Clear topcoats are not recommended for use over Concrete & Garage Recoat Primer.

SURFACE PREPARATION

For a previously painted, coated, stained, or sealed concrete surface, use a wire brush to remove any loose or peeling paint. Rinse or sweep away dust and other particles. Clean the entire floor with Rust-Oleum Cleaner & Degreaser. Sand (60-80 grit) or spot etch all exposed concrete surfaces using Rust-Oleum Clean & Etch. Rinse thoroughly and allow to dry completely.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Concrete & Garage Recoat Primer is ready to use. Do not thin. Apply only when air (ambient) temperature is between 50-90°F (10-32°C) and the relative humidity is below 85%. Do not paint outdoors if rain is expected within 24 hours. Stir thoroughly before applying.

Use a brush or edger to trim the perimeter and hard-to-reach areas. Use a long handled extension pole and a high quality 3/8" nap roller cover to apply an even coat of Rust-Oleum Concrete & Garage Recoat Primer onto the surface. Apply in 4'x4' foot sections and maintain a wet edge while rolling. Continue applying in 4'x4' sections until complete. Do not let product puddle. Only one coat is recommended.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Dry times increase at cooler temperatures. Concrete & Garage Recoat Primer must be allowed to dry a minimum of 6 hours, but no more than 48 hours, to ensure proper adhesion of topcoat.

CLEAN-UP

Wash tools and equipment with warm water and a mild detergent immediately after use. Properly dispose of all soiled rags. Store in a cool, dry area and do not let product freeze.

COVERAGE

Covers up to 400 sq. ft. per gallon on previously sealed, painted, coated, or smooth concrete floors. Rough or porous surfaces will require more material.

	TECHNICAL DATA	ROC-181
• TRUSTED QUALITY SINCE 1921 • 	RUST-OLEUM® CONCRETE & GARAGE RECOAT PRIMER	

PHYSICAL PROPERTIES

		CONCRETE & GARAGE RECOAT PRIMER
Resin Type		Acrylic
Pigment Type		Titanium Dioxide, Carbon Black
Solvents		Water, Propylene Glycol
Weight	Per Gallon	11.2 lbs.
	Per Liter	1.34 kg
Solids	By Weight	49.3%
	By Volume	28.6%
Volatile Organic Compounds		<100 g/l
Recommended Dry Film Thickness (DFT)		1-2 mils (25-50μ)
Wet Film to Achieve DFT (unthinned material)		4-7 mils (100-175μ)
Practical Coverage at Recommended DFT		200-400 sq.ft./gal Coverage rate can vary depending on the texture and porosity of the concrete
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Top Coat	After a minimum of 6 hours and before 48 hours
	Full Traffic	72 hours
Shelf Life		2 years
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.