



RUST-OLEUM® VINYL WRAP CLEAR

DESCRIPTION AND USES

Rust-Oleum® Vinyl Wrap Gloss Clear is a removable vinyl coating that provides endless customization for automotive and other applications. It provides a smooth, glossy finish with premium performance and protection from road debris and gasoline. This all-weather coating is great for use on metal, OEM clear coat, glass and more.

Apply Rust-Oleum Vinyl Wrap Gloss Clear over Rust-Oleum Vinyl Wrap colors. Not intended for use over any other products or surfaces. Vinyl Wrap can be removed when no longer needed or desired.

NOTE: NOT RECOMMENDED FOR USE ON PLASTICS. This product may not be compatible with all surfaces and all conditions surrounding application. Before applying to any surface, always test product in a small, inconspicuous area.

PRODUCT

| SKU | DESCRIPTION (11 oz.) |
|------------|-----------------------------|
| 363547 | Gloss Clear |

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

APPLICATION CONDITIONS

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to galvanized metal. Not recommended for automotive surfaces with a damaged OEM finish. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Thoroughly wash surface with soap and water prior to application. Let dry. Priming is not required or recommended.

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE**. Contact Rust-Oleum. Shake often during use. Keep the can 8-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Apply 4 or more light coats to build desired coating thickness, followed by 1 or more medium coat(s) to achieve a smooth final film.

NOTE: Target 50% coverage on first coat. Allow coating to dry for about 5 minutes between coats. More coats will result in a thicker coating which is easier to remove when desired. Allow coating to cure for 48 hours prior to washing.

DRY & RECOAT

Dry and recoat times are based on 70°F (20°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 30 minutes, to handle in 2 hours.

REMOVAL

You can peel film off once the coating has fully cured. This coating has been formulated for temporary use and is recommended to be removed within 6 months or less. A microfiber cloth or acetone may assist in the removal of coating in intricate areas.

CLEAN-UP

When finished spraying, clear spray valve by turning can upside down and pushing spray button for 5 seconds. Allow wet paint to dry, once dry, peel away or clean up with acetone. Throw empty cans in trash pickup. Do not burn or place in home compactor.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as acetone. Do not stick a pin or other objects into the stem.



**RUST-OLEUM®
VINYL WRAP CLEAR**

PHYSICAL PROPERTIES

| | | VINYL WRAP CLEAR |
|--|---------------|--|
| Resin Type | | Vinyl |
| Solvents | | Blend of Glycol Ethers, Acetates and Ketones |
| MIR | | 1.60 Max |
| Fill Weight | | 11 oz. |
| Practical Coverage Rate | | 2-4 sq. ft./can |
| Dry Times at 77°F (25°C) and 50% Relative Humidity* | Touch | 30 minutes |
| | Handle | 2 hours |
| | Recoat | Within 30 minutes |
| Shelf Life | | 2 years |
| Dry Heat Resistance | | 200°F (93°C) |
| Flash Point | | -156°F (-104°C) |
| Safety Information | | See SDS |

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.