

	TECHNICAL DATA	PT2X-07
	PAINTER'S TOUCH® 2X ULTRA COVER® HIGH GLOSS FINISH SPRAYS	

DESCRIPTION AND USES

Painter's Touch® 2x Ultra Cover® contains technology that provides twice the coverage on wood, metal, most plastic, wicker and more when compared to other matching colors of Rust-Oleum® general purpose paints: Painter's Touch, SPRAY N GO, Quick Color and Touch 'n tone. It covers surfaces with less spray passes, allowing projects to be completed faster and easier. Any angle spray feature allows you to spray in any direction, even upside down. Fast Drying.

TIP: Some plastics made of polyethylene such as plastic storage containers are manufactured in a way that may hinder maximum paint adhesion. Test paint in a hidden area first.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
331171	High Gloss White
331172	High Gloss Black
331173	High Gloss Citrus Fields
331174	High Gloss Prickly Pear
331175	High Gloss St. Tropez
331176	High Gloss Desert Ross
331177	High Gloss Morning Waterfall
331179	High Gloss Tropical Leaf
331180	High Gloss Strawberry Fields
348855	High Gloss Fiery Orange
348856	High Gloss White Sand
355057	High Gloss Macaw Blue
355060	High Gloss Thunder Cloud
366989	High Gloss Emerald Isle
372272	High Gloss Majestic Red

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRIMING

Use of Painter's Touch 2X Ultra Cover® primer provides superior adhesion and hiding and is especially recommended for bare wood and metal.

APPLICATION

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not use on objects that may exceed 200°F (93°C) surface temperature. Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after mixing ball begins to rattle. If mixing ball fails to rattle, DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart.

NOTE: On plastic maximum paint adhesion and durability is achieved in 5-7 days.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20 minutes, to handle in 1 hour, and is fully dry in 24 hours. Apply a second coat or clear coat within 1 hour or after 48 hours. Apply clear in 2-3 light coats a few minutes apart.

CLEAN-UP

When finished spraying, wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick pin or other object into the stem.

	TECHNICAL DATA	PT2X-07
	PAINTER'S TOUCH® 2X ULTRA COVER® HIGH GLOSS FINISH SPRAYS	

PHYSICAL PROPERTIES

2X ULTRA COVER HIGH GLOSS SPRAYS		
Resin Type	Alkyd, Urea Aldehyde	
Pigment Type	Mica	
Solvents	Acetone, Acetates	
MIR	Max 0.95	
Fill Weight	12 oz.	
Recommended Dry Film Thickness (DFT) per Coat	1.0-2.0 mils (25-50μ)	
Practical Coverage at Recommended DFT (assume 15% material loss)	10-15 sq.ft./can (0.9-1.4 m ² /can)	
Dry Times at 70F (21°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	Within 1 hour or after 48 hours
Dry Heat Resistance	200°F (93°C)	
Shelf Life	5 years	
Flash Point	-156°F (-104°C)	
Safety Information	For additional information, see SDS	

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 877-385-8155
www.rustoleum.com

Form: ARJ-1519
Rev.: 100623